

## **NEW WORK GLOSS**

**Dulux Trade** New Work Gloss is specifically formulated for the demanding requirements of new substrates. It gives a tough and durable mirror-like finish. It is the ideal partner for **Dulux Trade** New Work Undercoat, being easy to apply with excellent coverage and flow-out of brush marks.

### **KEY BENEFITS**

- Ideal for New Surfaces
- Excellent Opacity & Sharp Edge Cling
- Coverage up to 18m<sup>2</sup> Per Litre

### **PRODUCT INFORMATION**

#### **Typical Use**

Suitable for use on interior and exterior wood and metal surfaces.

#### **Pack Size**

5L.

#### **Colour Range**

White only.

#### **Film Properties**

***Chemical Resistance:*** Resistant to mild chemical fume attack, but where there is heavy attack, such as actual contact with chemicals, specialist paint systems may be required (contact the **AkzoNobel** Technical Advice Centre).

***Heat Resistance:*** Generally resistant to heat up to 90°C, but some discolouration of light colours may occur at elevated temperatures.

***Water Resistance:*** Resistant to the levels of atmospheric humidity present in normal interior and exterior environments and will withstand repeated washing. Not suitable for use on

immersed surfaces or where there is very heavy and prolonged condensation.

#### **Film Thickness**

*Film thickness will be dependent on the coverage achieved.*

***Wet:*** 50 microns.

***Dry:*** 25 microns.

#### **Composition (nominal)**

***Pigment:*** Lightfast Pigments.

***Binder:*** Alkyd.

***Solvent:*** White Spirit.

#### **Volume Solids**

64%.

### **SURFACE PREPARATION**

To get the best results, ensure surfaces to be painted are sound, clean and dry (new surfaces particularly must be fully dry) and free from all defective or poorly adhering material such as dirt, grease or wax.

New or bare surfaces should be primed with an appropriate **Dulux Trade** primer.

Thoroughly rub down previously painted surfaces, using 'wet flattening' methods where possible, then wipe off with a damp, lint free cloth. Special precautions should be taken during surface preparation of pre-1960s paint surfaces over

# NEW WORK GLOSS

wood and metal as they may contain harmful lead.

Treat any knots in wood with an appropriate knotting solution. Any surface defects should be filled with the appropriate **Polycell Trade Polyfilla**.

## SYSTEMS INFORMATION

STIR THOROUGHLY BEFORE USE. Apply 1 coat of **Dulux Trade** New Work Undercoat, followed by 1 or 2 coats of **Dulux Trade** New Work Gloss. For improved opacity on rough or textured surfaces, apply 2 coats of **Dulux Trade** New Work Undercoat.

**NOTE:** Whilst leading-edge technology has been used in the development of this product, the nature of white solvent-based paints means that they will all discolour over time. The rate of discolouration is faster on areas with no or low natural or UV light. For longer-lasting whiteness, we recommend the use of a water-based formulation such as **Dulux Trade** Quick Dry Gloss.

## APPLICATION METHOD

Brush or roller only. For Health & Safety reasons relating to all solvent-based paints, spray application is not recommended.

As with all solvent-based paints, do not apply at temperatures below 5°C (as recommended by British Standard BS 6150).

## Practical Coverage

A guide to the practical coverage which can be achieved under normal conditions is up to 18m<sup>2</sup> per litre.

## Spray Recommendations

This product should not be sprayed.

## Drying Times

*Single coat at standard thickness:*

**Touch Dry:** 4-6 hours.

**Recoat:** 16-24 hours.

## Cleaning Up

After use, remove as much product as possible from equipment before cleaning with brush cleaner.

When this paint container is empty please ask your stockist about recycling. If you have leftover paint, please dispose of it responsibly and consider donating it to **Community RePaint**. Find out more at [duluxtrade.co.uk/pp](http://duluxtrade.co.uk/pp).

## Transportation & Storage

Do not use or store in extremes of temperature and protect from frost. To prevent spillage, please store and transport upright.

## VOC

EU limit value for this product (cat.: A/d): 300g/l (2010). This product contains max. 300g/l VOC. VOC content: High (25-50%).



Issued 02/14

424

## NEW WORK GLOSS

### FURTHER SUPPORT

If you need further support, please contact the **AkzoNobel** Technical Advice Centre on 0333 222 70 70.

*Always read full Health, Safety & Environmental Information on can before use.*

Safety datasheet (SDS 424) is available free on request by telephoning the **AkzoNobel** Technical Advice Centre or by visiting [duluxtrade.co.uk](http://duluxtrade.co.uk).

AkzoNobel, the AkzoNobel logo, the Flourish logo, Dulux Trade, Polycell, Polyfilla, Community RePaint and the Planet Possible logo are trademarks of the AkzoNobel group. © AkzoNobel 2014.



At Dulux Trade, we believe by working with our customers we can reduce waste and do more with the resources we have. Together we can create a better future for our planet. Join us at [duluxtrade.co.uk/pp](http://duluxtrade.co.uk/pp)

**AkzoNobel**