

Issued 05/14

# **ANTI GRAFFITI CLEARCOAT**

**Dulux Trade** Anti Graffiti Clearcoat is a two pack, water-based coating for use over existing sound coatings or clean, dry and laitance free uncoated masonry surfaces. **Dulux Trade** Anti Graffiti Clearcoat dries to a tough gloss finish that has good impact and abrasive properties, protecting areas that are prone to graffiti. **Dulux Trade** Anti Graffiti Clearcoat can be used in areas where low odour coatings are required such as hospitals, schools and public buildings.

#### **KEY BENEFITS**

- Extra Durability
- Primed or Previously Coated Surfaces
- Interior & Exterior Use

#### PRODUCT INFORMATION

## **Typical Use**

Suitable for use over existing sound coatings or clean, dry and laitance free uncoated masonry surfaces. *NOTE:* Do not apply over underbound coatings such as distemper or non cross-linked flexible coatings such as Acrylated Rubber or Chlorinated Rubber.

#### **Pack Size**

3.91L Base and 1.09 Activator.

#### **Colour Range**

N/A.

#### **Film Properties**

Film thickness will be dependent on the coverage achieved.

*Wet:* 75 microns. *Dry:* 30 microns.

# **Composition (nominal)**

Pigment: N/A.

Binder: Polyacrylic/Isocyanate.

Solvent: Water.

#### **Volume Solids**

40% (nominal).

#### SURFACE PREPARATION

To get the best results, ensure surfaces to be painted are sound, clean and dry (new surfaces particularly must be fully dry) and free from any contaminants such as loose particles, dust and grease. It is recommended that a small test area is applied before treating the entire surface to ensure compatibility,

Special precautions should be taken during surface preparation of pre-1960s paint surfaces over wood and metal as they may contain harmful lead.

## **SYSTEMS INFORMATION**

SITR THOROUGHLY BEFORE USE. Apply 1 or 2 coats of **Dulux Trade** Anti Graffiti Clearcoat to sound, clean surfaces. Avoid over application.

*Mixing Ratio:* Supplied in correct proportions.

Add all of the Activator to the Base container and



# **ANTI GRAFFITI CLEARCOAT**

mix thoroughly for at least 5 minutes, until the product is smooth and even. DO NOT MIX PART UNITS. Badly activated or incorrectly mixed materials will affect performance and may cause early failure or discolouration.

**Pot Life:** 1-2 hours (depending on prevailing conditions).

#### **APPLICATION METHOD**

Apply by brush or roller only. FOR HEALTH AND SAFETY REASONS THIS PRODUCT MUST NOT UNDER ANY CIRCUMSTANCES BE APPLIED BY SPRAY.

#### **Practical Coverage**

A guide to the theoretical coverage which can be achieved is up to 8m² per litre.

#### **Thinning**

Ready for use when mixed. If required, add a maximum of 1 part clean water to 10 parts activated paint.

#### **Spray Recommendations**

For Health & Safety reasons, this product must not under any circumstances be applied by spray.

# **Drying Times**

Single coat at standard thickness:

Touch Dry: At 20°C - 6 hours.

**Recoat:** Minimum 16 hours and maximum 7 days. Hard dry after 16 hours.

#### Cleaning Up

After use, remove as much product as possible from equipment before cleaning with water.

When this paint container is empty please ask your stockist about recycling. If you have leftover paint, please dispose of it responsibly. Find out more at *duluxtrade.co.uk/pp*.

#### **Transportation & Storage**

Do not use or store in extremes of temperature and protect from frost. To prevent spillage, please store and transport upright.

#### VOC

EU limit value for this product (cat.: A/j): 140g/l (2010). This product contains max. 80g/l VOC. VOC Content: Medium (8-24.99%).

### **FURTHER SUPPORT**

If you need further support, please contact the AkzoNobel Technical Advice Centre on 0333 222 70 70.

Always read full Health, Safety & Environmental Information on can before use.



**Issued 05/14** 

# **ANTI GRAFFITI CLEARCOAT**

<u>Safety datasheet (SDS 816) is available free on request</u> by telephoning the **AkzoNobel** Technical Advice Centre or by visiting *duluxtrade.co.uk.* 

AkzoNobel, the AkzoNobel logo, the Flourish logo, Dulux Trade and the Planet Possible logo are trademarks of the AkzoNobel group. © AkzoNobel 2014.