



## Sikkens Rubbol XD Gloss

White

### About this product

Rubbol XD Gloss is an exceptionally durable high build, high gloss, solvent-borne opaque coating for exterior and interior timber joinery and trim, suitably primed metals and hard plastics. Rubbol XD Gloss is not recommended for use indoors as its drying times may be extended

### Key Benefits

- ✓ Advanced performance with outstanding gloss retention
- ✓ Optimum durability - up to 8 - 10 years maintenance cycle
- ✓ Retains all the application benefits of traditional solvent-borne products

### Special Features

- ✓ Durable

### Technical Information

Touch dry	6-7 hours
Recoatable	24 hours
Coverage	12-14 m <sup>2</sup> /L

### Product Information

#### Composition

Alkyd, Solvent-based

#### Key Benefits

Advanced performance with outstanding gloss retention, Optimum durability - up to 8 - 10 years maintenance cycle, Retains all the application benefits of traditional solvent-borne products

### **Colour Range**

CUPRINOL Digital Default Colors (Web Only)

### **Pack size**

1L, 2.5L

## **Application Method**

Conditions: Do not apply if there is a risk of rain, or when air/substrate temperatures are below 5°C or above 30°C during application or drying periods. Protect from frost and rain until dry. Failure to meet these requirements may adversely affect the drying, visual quality and durability of the finish. Initial procedure Ensure product is thoroughly stirred before and during application, otherwise sheen and colour variations may be experienced. We do not recommend thinning Rubbol XD Gloss. Excessive thinning will reduce opacity.

Applying the product : For best results use a good quality, long-haired, soft bristle brush.

Two coats of Rubbol XD Gloss should be applied, allowing a minimum of 24 hours drying time between coats. On new work,

where practical, the first coat should be applied all round prior to fixing. Pay special attention to any areas of exposed end

grain, tops and bottoms of doors, and undersides of cills. The second coat should be applied to all exposed surfaces, as

soon as possible after the first coat has dried, but no sooner than 24 hours and within 48 hours, in order to provide full

protection. In any event this period should not extend beyond three months, otherwise additional preparation and coating may be necessary. If applied to exterior wood and the contract is of long duration, it is suggested that a further coat be applied prior to hand over to make good any weathering during the construction period. If the second coat is not applied

within 48 hours, light sanding with a medium grade abrasive, to provide a surface "key" will be required.

Ensure all dust is removed. The product should be applied in a full flowing coat, laying off in the direction of the grain, using the minimum number of brushstrokes necessary to produce an acceptable finish.

Avoid overbrushing, as this will reduce the protection afforded. Apply to a wet film thickness of approximately 70 micrometres. The wet film thickness should be greater than 65 micrometres but not more than 75 micrometres.