



Hammerite Kurust

About this product

Kurust transforms rust to a sound surface in 15 minutes. Ideal for small areas of rust, stone chips and scratches.

Key Benefits

- ✓ Can be topcoated after only 3 hours
- ✓ No primer or undercoat required
- ✓ Simple to apply - no need to rinse off
- ✓ Converts iron oxide to stable iron complexes.

Special Features

- ✓ Surface can be topcoated after only 3 hours
- ✓ No need for primer or undercoat

Technical Information

Touch dry	3 hours
Recoatable	3 hours
Coverage	20-25m ² per litre

Product Information

Typical Use

Clean surface by removing all loose paint and rust, dirt, grease and salt. Rinse with clean water and allow time to dry

Composition

Key Benefits

Can be topcoated after only 3 hours, No primer or undercoat required, Simple to apply - no need to rinse off, Converts iron oxide to stable iron complexes.

Pack size

12.5ML, 90ML, 250ML

System Information

Pencil brush - Shake container well. Using the brush in the cap apply directly onto the rusty area, working well into any pitted areas, corners and edges. 100/250ml - Shake container well and pour required amount into a plastic container. By brush: apply direct to rusty area, working well into heavily pitted areas, corners and edges. Avoid coating onto painted areas. Hammerite Kurust will turn blue/black when reacting with rust. If it does not change colour in 1 hour re-apply. Apply topcoat after 3 hours. Do not replace unused Kurust back into the original container.

Application Method

Pencil brush - Shake container well. Using the brush in the cap apply directly onto the rusty area, working well into any pitted areas, corners and edges. 100/250ml - Shake container well and pour required amount into a plastic container. By brush: apply direct to rusty area, working well into heavily pitted areas, corners and edges. Avoid coating onto painted areas. Hammerite Kurust will turn blue/black when reacting with rust. If it does not change colour in 1 hour re-apply. Apply topcoat after 3 hours. Do not replace unused Kurust back into the original container.